

# **Application Notes & Product Data Sheet**

## Primary Batteries— Alkaline, & Heavy Duty

#### I. General Information

#### **Definition of a Battery**

A battery is a portable energy source that is made up of three basic components—an anode, a cathode and an electrolyte.

The anode is the negative portion of the battery, the cathode is the positive portion and the electrolyte is a liquid solution that aids in the flow of energy.

These three components can be made up of many different materials and combined in an almost endless array of sizes and shapes. The choice of materials used, and the quality, grade and density of these materials will play a major role in determining the energy levels and performance of batteries.

## II. Chemical Systems and Construction

Primary batteries were first made in the mid-1800's. These early batteries were known as zinc carbons. Zinc carbon technology is still around but it has been updated with purer, quality grade materials and a different electrolyte. This formulation is now called zinc chloride (heavy duty).

Today, many designers choose alkaline manganese batteries. These batteries provide a much higher energy output which is needed for the fast growing demand for portable power.

Rayovac has played an important role in this battery history. Founded in 1906, Rayovac is an international manufacturer and marketer of alkaline, and heavy duty batteries.

#### **Alkaline**

Alkaline batteries provide the longest service life for high drain devices. They will last more than twice as long as heavy duty batteries in certain applications. Alkaline batteries get their long life from their unique construction and the purity of the materials used. (Diagram 1)

The alkaline cathode is a mixture of manganese dioxide, graphite, and electrolyte. This mixture is granulated, aged in storage, and then compacted into a pressed cylindrical assembly. This mixture is inserted into a steel can. The steel can and the mixture become the cathode of the alkaline battery. An indentation is made near the top of the can and sealant is placed just above it. These two steps help safeguard the battery against leakage.

#### Cutaway of an Alkaline Battery




Diagram 1

If the cathode and anode come in contact with each other, a very active chemical reaction would occur. A barrier must be between the two. A paper separator soaked with an electrolyte that promotes ionic or electrolytic conductivity is used as this barrier. The anode portion is a gel made up of zinc powder and several other materials. The anode is then inserted into the steel can against the paper separator.

To insure a long shelf life, the battery must be sealed. The seal is made of a brass nail (which acts as the current collector), a plastic gasket, a steel washer and metal endcap. The four items are preassembled and inserted into the middle of our steel can up against the indentation (which was formed earlier). A top plate is welded to the other end of the can to provide the positive polarity safety feature.

The batteries are then stored, given another voltage test and a decorative, insulating outer label is applied.

Rayovac has further developed the alkaline system and introduced Rechargeable Alkaline™ Batteries. (Refer to OEM Designer's Guide OEM-150)

#### Zinc Chloride

Heavy duty zinc chloride batteries are the result of technological advances in zinc carbon battery manufacturing.

The type and purity of the mix ingredients is why a zinc chloride battery lasts up to twice as long as the older zinc carbon formulations. (Diagram 2)

A powdery mix serves as the cathode component of the zinc chloride battery. The mix is made of manganese dioxide (the active ingredient), carbon black (for electrical conductivity and moisture absorption), and zinc chloride electrolyte (which assists the chemical reaction).

#### **Cutaway of a Zinc Chloride Battery**




Diagram 2

The anode portion of a zinc chloride battery is a pure zinc can. Besides acting as the anode, the zinc can also serves as a container for the remaining battery components.

A paper separator and bottom cup is used to keep the components from coming in contact with each other.

	Alkaline	Heavy Duty		
Chemical System	Alkaline Manganese	Zinc Chloride		
Features	Best for high drain Best for mapplications drain appl			
Applications	<ul> <li>CD Players</li> <li>Camera Flash</li> <li>Calculators</li> <li>Cassette Players</li> <li>Flashlights</li> <li>Toys</li> <li>Smoke Detectors</li> </ul>	<ul> <li>Portable Radios</li> <li>Smoke Detectors (only when recommended by manufacturer)</li> <li>Calculators</li> <li>Clocks</li> <li>Toys</li> <li>Remote Control Units</li> </ul>		

Table 1



The mix is then inserted in the can. A compression washer is placed on top and a carbon rod is inserted through the mix. This carbon rod serves as the current collector for the battery and provides the outside contact.

Next, the top of the zinc can is curled inward. The battery is placed inside a paper tube that has a metal bottom plate. A seal washer is placed on top of the carbon rod. Finally this entire assembly is placed inside a protective outer shell.

The paper tube acts as an electrical insulator, keeping the negative and positive ends of the battery from contacting the outside protective shell. The shelled battery is then sealed which keeps the internal components of our battery fresh.


Finally, a metal cap (the positive contact of our battery) is embedded on top of the battery and the metal shell is curled over the cap.

## III. Recommended Usage of Chemical Systems

Rayovac offers top performing, quality built alkaline, and heavy duty batteries enabling you to meet every power requirement you have. Table 1 describes the features and applications of these two systems.

The open circuit voltage of fresh cylindrical batteries is approximately 1.55 volts. The closed circuit voltage declines gradually as a function of the depth of discharge; therefore, greater hours of service are obtained as the functional end point is lowered.


Figure 1 illustrates the typical service life to 0.9 volts of a AA Alkaline and Heavy Duty battery on a cassette player used one hour per day. Figure 2 outlines the number of service hours versus current drain to 0.9 volts



### IV. Technical Data

	Alkaline	Heavy Duty
Nominal Voltage/Cell	1.5 volts	1.5 volts
Maximum Continuous Current	High	Medium
Maximum Pulse Current	High	Medium
Temperature Range	-30°C to 55°C (-20°F to 130°F)	-20°C to 55°C (0°F to 130°F)
Capacity Retention	Greater than 97% after 12 months @ 21°C (70°F) Greater than 85% after 5 years	Greater than 93% after 12 months @ 21°C (70°F) Greater than 85% after 4 years

Table 2



## V. Rayovac Batteries and The Environment

All Rayovac batteries, alkaline, and heavy duty, use a no Mercury added formulation. Rayovac alkaline and zinc chloride batteries do not contain Cadmium as an active ingredient.

Rayovac Alkaline and Heavy Duty batteries are recognized by the U.S. Environmental Protection Agency (EPA) as standard, household waste. Worldwide regulations vary from country to country. Contact Rayovac's Environmental and Safety Department or the OEM/Technical products group for the latest environmental updates and legislation.

### VI. Storage

Batteries depend on internal chemical reactions to produce power. Chemical reactions are accelerated by high temperatures and retarded by low temperatures. Therefore, to minimize power loss during storage, batteries should ideally be stored at a maximum temperature of 77°F (25°C). Refrigerated storage is neither necessary nor recommended.

The following storage procedures should be observed to assure maximum battery power.

- 1. Rotate inventory stock. Make sure your customer receives the freshest possible product by rotating your stock on a "first in first out" basis.
- 2. Avoid storage in high temperature areas. Make sure that batteries are stored away from radiators, hot air vents, motors, and equipment that generates heat. Do not store batteries near windows where sunlight could heat up the batteries.

## VII. Handling and Shipping

Batteries are vulnerable to short circuiting if not handled properly. Those battery types which have their "+" and "-" terminations in close proximity to each other are particularly susceptible to short circuiting. Examples of these battery types are the Rayovac A1604, and D1604 batteries. Rayovac packaging engineers design all packaging to assure that Rayovac batteries can be shipped and stored in their original cartons without damage.

To avoid potential short circuit and shipping damage situations:

- 1. Always store the batteries in the trays and/or cartons in which they were shipped.
- 2. Whenever possible, re-ship the batteries in their original trays and/or cartons.
- 3. Broken package shipments of Rayovac batteries can be safely made by putting each battery in a sealed plastic bag.
- 4. General precautions:
  - A. Never place or dump batteries on conducting surfaces, such as metal tables or shelves.
  - B. Never ship batteries in anti-static bags or conductive foam as these materials will short out the battery.
  - C. Insulate metal micrometers and calipers with non-conductive tape to avoid short circuiting batteries during dimensional checks.

If you have any questions please contact your Rayovac sales representative.



## **VIII. Dimensional Specifications**

#### A. Alkaline

#### a. AAA Size Alkaline Battery

Rayovac No.: 824 Nominal Voltage: 1.5 volts

System: Primary Alkaline

ANSI/NEDA No.: 24A (AAA) IEC No.: LR03

Approximate Volume: 0.2 cu. in. (3.3 cu. cm.)


Approximate Weight: 0.4 oz. (11 gm.)
Terminals: Flashlight

Shell: Flashligh Plastic

Environmental: Meets Environmental

Protection Agency (EPA) requirements for landfill disposal. No mercury added

formulation.



	Load	Current	Estimate		ge Servi	ce At 70°F (Hours) age	Approx. mAh Capacity
Application & Duty Cycle	(ohms)	(mA at 1.2V)	1.2V	1.1V	1.0V	0.9V	to 0.9V
Radio (4 Hrs/Day)	75	16	47	54	63	68	1123
Cassette (1 Hr/Day)	10	120	3	6	7	8	958
Cassette (Continuous)	10	120	2	6	7	8	963
Flashlight (4 Min/Hr – 8 Hrs/Day)	5.1	235	1	2	3	4	834
Photo (15 Sec/Min – 24 Hrs/Day)	3.6	333	_	_	_	666	841



#### b. AA Size Alkaline Battery

Rayovac No.: 815

Nominal Voltage: 1.5 volts

System: Primary Alkaline

ANSI/NEDA No.: 15A (AA)
IEC No.: LR6

Approximate Volume: .48 cu. in. (7.87 cu. cm.)


Approximate Weight: 0.8 oz. (22.9 gm.)

Terminals: Flashlight Shell: Plastic

Environmental: Meets Environmental

Protection Agency (EPA) requirements for landfill disposal. No mercury added

formulation.



	Load	Current	Estimated	Approx. ) mAh _Capacity			
Application & Duty Cycle	(ohms)	(mA at 1.2V)	1.2V	1.1V	1.0V	0.9V	to 0.9V
Radio (4 Hrs/Day)	43	28	59	69	80	88	2535
Cassette (1 Hr/Day)	10	120	10	14	16	19	2216
Toy/Game (1 Hr/Day)	3.9	308	2	4	6	7	1907
Flashlight (Continuous)	3.9	308	2	4	5	6	1785
Photo (15 Sec/Min – 24 Hrs/Day	1.8	667	_	_	_	660	1646





#### c. C Size Alkaline Battery

Rayovac No.: 814

Nominal Voltage: 1.5 volts

System: Primary Alkaline

ANSI/NEDA No.: 14A (C) IEC No.: LR14

Approximate Volume: 1.6 cu. in. (26.2 cu. cm.)


Approximate Weight: 2.5 oz. (70 gm.)

Terminals: Flashlight Shell: Plastic

Environmental: Meets Environmental

Protection Agency (EPA) requirements for landfill disposal. No mercury added

formulation.



	Estimated Average Service At 70°F (Hours Load Current Cutoff Voltage						Approx. mAh Capacity
Application & Duty Cycle	(ohms)	(mA at 1.2V)	1.2V	1.1V	1.0V	0.9V	to 0.9V
Radio (4 Hrs/Day)	20	60	79	96	108	117	7245
Cassette (1 Hr/Day)	6.8	176	18	28	33	36	6365
Flashlight (4 Min/Hr – 8 Hrs/Day)	3.9	308	8	14	19	20	6133
Toy/Game (1 Hr/Day)	3.9	308	7	13	17	20	5822
Flashlight (Continuous)	3.9	308	5	11	16	19	5539



#### d. D Size Alkaline Battery

Rayovac No.: 813

Nominal Voltage: 1.5 volts

System: Primary Alkaline

ANSI/NEDA No.: 13A (D) IEC No.: LR20

Approximate Volume: 3.4 cu. in. (55.7 cu. cm.)

Approximate Weight: 5.0 oz. (144 gm.)


Terminals: Flashlight Shell: Plastic

Environmental: Meets Environmental

Protection Agency (EPA) requirements for landfill

disposal. No mercury added

formulation.



	Load	Estimated Average Service At 70°F (I Load Current Cutoff Voltage						
Application & Duty Cycle	(ohms)	(mA at 1.2V)	1.2V	1.1V	1.0V	0.9V	-Capacity to 0.9V	
Radio (4 Hrs/Day)	10	120	80	101	112	126	15,453	
Cassette (1 Hr/Day)	3.9	308	21	32	38	43	13,118	
Toy/Game (1 Hr/Day)	2.2	545	6	14	19	22	11,635	
Flashlight (4 Min/Hr - 8 Hrs/Day)	2.2	545	9	16	21	24	12,782	
Flashlight (Continuous)	2.2	545	6	12	17	21	10,600	
Flashlight, K2 Krypton Bulb (4 Min/14 Min - 8 Hrs/Day)	1.5	800	3	7	12	15	10,837	





#### e. 9-Volt Alkaline Battery

Rayovac No.: A1604 Nominal Voltage: 9 volts

System: Primary Alkaline

ANSI/NEDA No.: 1604A (9v) IEC No.: 6LR61

1.2 cu. in. (19.7 cu. cm.) Approximate Volume:


1.6 oz. (45.4 gm.) Approximate Weight:

Terminals: Snap Shell: Steel

**Environmental:** Meets Environmental

Protection Agency (EPA) requirements for landfill disposal. No mercury added

formulation.



Application &	Load	Current -	Estim	Approx. mAh — Capacity				
Duty Cycle		(mA at 7.2V)	7.8V	6.6V	6.0V	5.4V	4.8V	to 4.2V
Low Rate (Continue	ous) 6000	1	251	424	473	522	531	662
Radio (2 h/d)	620	12	12	39	44	48	52	609
Toy/Game (1 h/d)	270	27	3	16	18	20	22	569
Calculator (30 m/d)	180	40	2	10	12	13	14	551



### **B.** Heavy Duty

#### a. AAA Size Heavy Duty Battery

Rayovac No.: 3AAA
Nominal Voltage: 1.5 volts
System: Zinc Chloride
ANSI/NEDA No.: 24D (AAA)

IEC No.: R03


Approximate Volume: .2 cu. in. (3.3 cu. cm.)

Approximate Weight: 3 oz. (9 gm.)
Terminals: Flashlight
Shell: Plastic

Environmental: Meets Environmental

Protection Agency (EPA) requirements for landfill disposal. No mercury added

formulation.



	Load	Current	Estimated	70°F (Hours)	Approx. mAh Capacity		
Application & Duty Cycle	(ohms)	(mA at 1.2V)	1.2V	1.1V	1.0V	0.9V	to 0.9V
Radio (4 Hrs/Day)	75	16	25	29	31	33	550
Cassette (1 Hr/Day)	10	120	0.7	1.7	2.5	2.8	320
Flashlight (4 Min/Hr – 8 Hrs/Day	) 5.1	235	0.2	0.7	1.2	1.5	320
Photo (15 Sec/Min - 24 Hr/Day)	3.6	333	_	_	_	210 Pulses	s —





#### b. AA Size Heavy Duty Battery

Rayovac No.: 5AA

Nominal Voltage: 1.5 volts

System: Zinc Chloride

ANSI/NEDA No.: 15D (AA)

IEC No.: R6

Approximate Volume: 0.48 cu. in. (7.87 cu. cm.)

Approximate Weight: 0.65 oz. (18.4 gm.)


Terminals: Flashlight Shell: Steel

Environmental: Meets Environmental

Protection Agency (EPA) requirements for landfill

disposal. No mercury added

formulation.



	Load	Current	Estimated	70°F (Hours)	Approx. mAh Capacity		
Application & Duty Cycle	(ohms)	(mA at 1.2V)	1.2V	1.1V	1.0V	0.9V	to 0.9V
Radio (4 Hrs/Day)	43	28	27	33	36	37	1100
Cassette (1 Hr/Day)	10	120	4.2	5.7	6.8	7.7	925
Toy/Game (1 Hr/Day)	3.9	256	0.4	1.1	1.7	2.2	635
Photo (15 Sec/Min – 24 Hrs/Day	1.8	667	_	_	_	194 Pulses	· —



#### c. C Size Heavy Duty Battery

Rayovac No.: 4C

Nominal Voltage: 1.5 volts
System: Zinc Chloride
ANSI/NEDA No.: 14D (C)

IEC No.: R14

Approximate Volume: 1.6 cu. in. (26.2 cu. cm.)


Approximate Weight: 1.5 oz. (50 gm.)

Terminals: Flashlight Shell: Steel

Environmental: Meets Environmental

Protection Agency (EPA) requirements for landfill disposal. No mercury added

formulation.



	Load	Current	Estimated	Approx. mAh Capacity			
Application & Duty Cycle	(ohms)	(mA at 1.2V)	1.2V	1.1V	1.0V	0.9V	to 0.9V
Radio (4 Hrs/Day)	20	60	33	40	43	44	2780
Cassette (1 Hr/Day)	6.8	176	6.7	10.9	13.7	14.5	2550
Flashlight (4 Min/Hr – 8 Hrs/Day	) 3.9	308	2.4	5.0	7.3	8.2	2400
Toy/Game (1 Hr/Day)	3.9	308	1.7	4.3	6.6	7.8	2230





#### d. D Size Heavy Duty Battery

Rayovac No.: 6D

Nominal Voltage: 1.5 volts
System: Zinc Chloride

ANSI/NEDA No.: 13D (D) IEC No.: R20

Approximate Volume: 3.4 cu. in. (55.7 cu. cm.)


Approximate Weight: 3.3 oz. (96 gm.)

Terminals: Flashlight Shell: Steel

Environmental: Meets Environmental

Protection Agency (EPA) requirements for landfill disposal. No mercury added

formulation.



	Load	Estimated Average Service At 70°F (Hour oad Current Cutoff Voltage					
Application & Duty Cycle	(ohms)	(mA at 1.2V)	1.2V	1.1V	1.0V	0.9V	- Capacity to 0.9V
Radio (4 Hrs/Day)	10	120	36	47	53	56	6880
Cassette (1 Hr/Day)	3.9	308	7.8	13.4	17.7	20.5	6075
Flashlight, PR2 Vacuum Bulb (4 Min/Hr - 8 Hrs/Day)	2.2	545	2.4	5.2	8.5	10.9	5470
Toy/Game (1 Hr/Day)	2.2	545	1.6	4.4	7.1	9.5	4725



#### e. 9-Volt Heavy Duty Battery

Rayovac No.: D1604 Nominal Voltage: 9 volts

System: ZINC CHLORIDE

ANSI/NEDA No.: 1604D (9v)

IEC No.: 6F22

Approximate Volume: 1.2 cu. in. (19.7 cu. cm.)

Approximate Weight: 1.5 oz. (42.5 gm.)


Terminals: Snap Shell: Steel

Environmental: Meets Environmental

Protection Agency (EPA) requirements for landfill

disposal. No mercury added

formulation.



Application &	Load	Current	Estimate		ge Servic Itoff Volta	e At 70°F ige	(Hours)	Approx. mAh Capacity
Duty Cycle	(ohms)	(mA at 7.2V)	7.8V	6.6V	6.0V	5.4 <b>V</b>	4.2V	to 4.2V
Low Rate (24 Hrs/Day)	6000		188	326	351	364	385	485
Radio (2 Hrs/Day)	620	12	7.7	25.5	31.3	35.1	39.1	435
Toy/Game (1 Hr/Day)	270	27	0.9	7.5	10.3	12.2	16.6	390
Calculator (30 Min/Day)	180	40	0.3	3.7	5.5	7.2	10.3	350
Cassette (1 Hr/Day)	180	40	0.3	3.5	5.5	7.1	10.3	350






## IX. Product Availability

Rayovac batteries are available in various packaging options including bulk, carded, and multi-packs. For information, call your Rayovac representative.

#### **ENGINEERING NOTES**



#### Notice

This publication is furnished only as a guide. It is the user's responsibility to determine suitability of the products described for the user's purpose (even if the use is described herein) and to take precautions for protection against any hazards attendant to the handling and use of the products. Rayovac recommends prospective users test each application.

The battery products and arrangements described herein may be covered by patents owned by Rayovac or others. Neither this disclosure nor the sale of products by Rayovac conveys any license under patent claims covering combinations of battery products with other elements or devices. Rayovac does not assume liability for patent infringement arising from any use of the products by the purchaser.

The technical data contained herein are not designed to be the basis for specifications. Rayovac's Quality Assurance Department can furnish data that can serve as the basis for specifications.



#### **Worldwide Sales & Marketing Offices**

RAYOVAC CORPORATION World Headquarters

World Headquarters DEM Sales & Marketing P.O. Box 44960 Madison, WI 53744-4960 Tel. (608) 275-3340 Fax (608) 275-4973 RAYOVAC CANADA INC. 5448 Timberlea Boulevard

Mississauga, Ontario L4W 2T7 Canada Tel. (905) 624-4448 Fax (905) 629-2571 RAYOVAC UK, LTD.

Galleon House King Street Maidstone, Kent ME14 1BG England Tel. 011-44-622-688331

Tel. 011-44-622-688331 Fax 011-44-622-685523 RAYOVAC FAR EAST LTD.

Room 720-723, Hollywood Plaza 610 Nathan Road Mongkok Kowloon Hong Kong Tel. 011-852-2782-2343 Fax 011-852-2782-4091

www.rayovac.com/oem

OEM 151 (R-3/10) CS39406

printed on recycled paper